

# CRAYVALLAC FLOW-100



---

## TECHNICAL DATA

### SALES SPECIFICATION

Non-volatile content at 150°C (%)      99 - 100  
(MOES1150)

### OTHER PROPERTIES

Appearance	Clear liquid
Colour, Hazen Scale	< 150
Density at 25°C (g/cm <sup>3</sup> )	1.02
Viscosity Noury at 25°C (Poises)	80-150

---

## PRODUCT INFORMATION

**CRAYVALLAC FLOW-100** is a high performance acrylic flow and levelling agent for the control of coating surface properties. The performance benefits of this product are:

- Enhances substrate wetting, flow and levelling
- Produces smoother films with fewer defects
- Suitable for most coating systems
- Contains no silicone ingredients
- Pourable
- 100% active

## RECOMMENDED AMOUNTS

Generally 0.2 – 2.0 % based on total resin solids

## INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

The current trend towards high-solids, solvent-free and powder coatings has reduced or eliminated the role of solvents to overcome the effects of poor substrate wetting and flow. This leads to coatings with an increased level of surface defects and often a reduction in substrate adhesion.

**CRAYVALLAC FLOW-100** has been developed especially to address these issues. This high performance product functions primarily by reducing

the surface energy of the coating to give enhanced substrate wetting and an improvement to flow and levelling. The following benefits are to be gained by using **CRAYVALLAC FLOW-100** in powder coatings and coatings in general e.g. solvent-based, high-solids and solvent-free:

- Enhanced substrate wetting
- Improved flow and levelling
- Reduced craters and fisheyes
- Reduced orange peel and pinholes

The results of these enhancements are smoother films with fewer imperfections and a superior overall appearance when compared with the unmodified coating. **CRAYVALLAC FLOW-100** can be added to coating formulations prior to, or during, the pigment dispersion stage; the presence of acrylic flow and levelling agents often results in improved pigment dispersion. **CRAYVALLAC FLOW-100** may also be added during the letdown either neat or pre-thinned in a suitable solvent to aid mixing.

For powder coating applications, **CRAYVALLAC FLOW-100** must be used indirectly following its dispersion in a suitable carrier. A common technique used is to dissolve **CRAYVALLAC FLOW-100** in molten polyester. Once cooled, the polyester/acrylic blend is then suitably granulated for dry blending with the other coating components prior to extrusion.

Due to the multitude of formulations, processing methods and application conditions used in the

field, we strongly recommend that all products containing **CRAYVALLAC FLOW-100** be tested thoroughly to ensure suitability for their intended end use.

### **PRECAUTION FOR STORAGE**

**CRAYVALLAC FLOW-100** should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 4 years after production date.

### **PRECAUTION FOR USE**

Please refer to the corresponding Safety Data Sheet.

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema  
420 rue D'Estienne d'Orves  
92705 Colombes Cedex - France  
[www.arkema.com](http://www.arkema.com)

[www.crayvallac.com](http://www.crayvallac.com)