

# CRAYVALLAC WN-2789



---

## TECHNICAL DATA

### SALES SPECIFICATION

Dropping Point (CR 010) 115-120°C (239-248°F)

### OTHER PROPERTIES

Appearance White powder

Particle Size (CR 015) DV. 5 5.0-7.0 µm

Max. particle size (CR 015) 30 µm

---

## PRODUCT INFORMATION

**CRAYVALLAC WN-2789** is a polyethylene compound conforming to FDA 175.300. It provides the following performance benefits:

- Excellent rub resistance with minimal effect on gloss
- High heat resistance
- Good solvent resistance
- Good mar resistance

**CRAYVALLAC WN-2789** is mainly suitable for use in powder coatings.

## RECOMMENDED AMOUNTS

Generally 0.5-3.0% based on total formulation

## INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

**CRAYVALLAC WN-2789** has been especially designed to give good surface properties to polyester and hybrid powder coating systems. This wax is easily incorporated using conventional pre-mixing techniques prior to extrusion.

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WN-2789** be tested thoroughly to ensure suitability for their intended end use.

## PRECAUTIONS FOR STORAGE

**CRAYVALLAC WN-2789** should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 4 years from production date.

## PRECAUTIONS FOR USE

Please refer to the corresponding Safety Data Sheet.

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema  
420 rue D'Estienne d'Orves  
92705 Colombes Cedex - France  
[www.arkema.com](http://www.arkema.com)

[www.crayvallac.com](http://www.crayvallac.com)