

## COATING RESINS

### TECHNICAL DATA

### CRAYVALLAC WN-2789

#### SALES SPECIFICATION

Dropping Point  
(CR 010)

90-100°C  
(194-212°F)

#### OTHER PROPERTIES

Appearance

prills

#### PRODUCT INFORMATION

**CRAYVALLAC WN-2789** is a polyethylene compound conforming to FDA 175.300. It provides the following performance benefits:

- Excellent rub resistance with minimal effect on gloss
- High heat resistance
- Good solvent resistance
- Good mar resistance

**CRAYVALLAC WN-2789** is mainly suitable for use in powder coatings.

#### PRECAUTION FOR USE

Please refer to the corresponding Safety Data Sheet.

#### RECOMMENDED AMOUNTS

Generally 0.5-3.0% based on total formulation

#### INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

**CRAYVALLAC WN-2789** has been especially designed to give good surface properties to polyester and hybrid powder coating systems. This wax is easily incorporated using conventional pre-mixing techniques prior to extrusion.

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WN-2789** be tested thoroughly to ensure suitability for their intended end use.

#### PRECAUTION FOR STORAGE

**CRAYVALLAC WN-2789** should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 4 years from production date.