

CRAYVALLAC WN-2950



TECHNICAL DATA

SALES SPECIFICATION

Dropping Point
(CR 010) 128-132°C

OTHER PROPERTIES

Appearance White powder

Particle Size (CR 015)
DV. 5 5.0-7.0 µm

PRODUCT INFORMATION

CRAYVALLAC WN-2950 is a very fine micronised polyethylene wax conforming to FDA 175.300. When used in printing inks, and other demanding applications, the following performance benefits are achieved:

- Imparts superior rub/mar resistance and slip properties with minimum effect on gloss.
- High melting point wax with high hardness, heat and solvent resistance.
- Particularly suited to “stir in” applications.

RECOMMENDED AMOUNTS

Generally 0.5-3.0% based on total formulation

INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

CRAYVALLAC WN-2950 is readily dispersed into coating formulations using a variety of techniques e.g. high-speed dispersers, bead mills and triple roll mills.

In general, micronised waxes are best incorporated into coating systems by pre-mixing with the binder. Alternatively, waxes may be added to the formulation immediately following the dispersion stage but prior to the final letdown.

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WN-2950** be tested

thoroughly to ensure suitability for their intended end use.

PRECAUTION FOR STORAGE

CRAYVALLAC WN-2950 should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 4 years from production date.

PRECAUTIONS FOR USE

Please refer to the corresponding Safety Data Sheet.

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema
420 rue D'Estienne d'Orves
92705 Colombes Cedex - France
www.arkema.com

www.crayvallac.com