

# CRAYVALLAC WS-8050



---

## TECHNICAL DATA

### SALES SPECIFICATION

Specific gravity  
(CR 006) 0.90 ± 0.01

### OTHER PROPERTIES

Appearance Low viscosity white dispersion

Viscosity @25°C  
(CR 008) Approx. 200 mPa.s.

Solid content  
(CR 009) Approx. 40 %

---

## PRODUCT INFORMATION

**CRAYVALLAC WS-8050** is a 40% active dispersion of polyethylene wax in butyl acetate, conforming to FDA 175.300. This product provides the following benefits when used in coating applications:

- Pre-dispersed and hence easy to incorporate
- Exceptional rub, abrasion and scratch resistance
- Exceptional slip, solvent and heat resistance
- Good surface hardness, toughness and anti-blocking
- Similar in performance to CRAYVALLAC WN-3025

The low viscosity and high active content of this dispersion, together with freedom from dust, assist the efficiency of manufacturing processes.

**CRAYVALLAC WS-8050** provides the formulator with the means of controlling the frictional characteristics of a coating as well as enhancing its surface protection properties.

**CRAYVALLAC WS-8050** is suitable for use in the following water-based and solvent-based applications:

- Inks
- Metal decorating
- Coil coatings
- General industrial coatings

The following summarises some of the potential applications for **CRAYVALLAC WS-8050**:

- In metal packaging, coil coating and general industrial coatings to improve slip, abrasion and rub resistance
- A matting agent – alone or in combination with silica

To retard the settlement and allow the re-dispersion of pigments

### RECOMMENDED AMOUNTS

Generally 1.0–6.0% based on total formulation.

### INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

**CRAYVALLAC WS-8050** is readily dispersed into coating formulations using a variety of techniques. It also retards the settlement of pigments and assists in their re-dispersion.

The use of pre-dispersed waxes, such as **CRAYVALLAC WS-8050**, avoids the inconveniences commonly associated with micronised powders. Dispersions by nature are also easier and more efficient to incorporate, as they require less intensive processing.

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WS-8050** be tested thoroughly to ensure suitability for their intended end use.

## **PRECAUTION FOR STORAGE**

**CRAYVALLAC WS-8050** should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 24 months from production date.

## **PRECAUTION FOR USE**

Please refer to the corresponding Safety Data Sheet.

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema  
420 rue D'Estienne d'Orves  
92705 Colombes Cedex - France  
[www.arkema.com](http://www.arkema.com)

[www.crayvallac.com](http://www.crayvallac.com)