

CRAYVALLAC WW-9790



TECHNICAL DATA

SALES SPECIFICATION

Specific gravity
(CR 006) 1.01 ± 0.01

OTHER PROPERTIES

Appearance Low viscosity white dispersion

Viscosity @25°C
(CR 008) Approx. 200 mPa.s.

Solid content
(CR 009) Approx. 25 %

PRODUCT INFORMATION

CRAYVALLAC WW-9790 is a 25% active dispersion of PTFE modified polyethylene in water. **CRAYVALLAC WW-9790** has been formulated for:

- Water-based inks and coatings
- Metal decorating
- Coil coating

This product imparts excellent slip, abrasion and rub resistance to aqueous inks and coatings.

Additionally, incorporation of the wax retards the settlement of pigments and assists in the re-dispersion.

The low viscosity and high active content of this dispersion, together with freedom from dust, assist the efficiency of manufacturing processes.

RECOMMENDED AMOUNTS

Generally 2.0–8.0% based on total formulation.

INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WW-9790** be tested thoroughly to ensure suitability for their intended end use.

PRECAUTION FOR STORAGE

CRAYVALLAC WW-9790 should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 24 months from production date.

PRECAUTION FOR USE

Please refer to the corresponding Safety Data Sheet.

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema
420 rue D'Estienne d'Orves
92705 Colombes Cedex - France
www.arkema.com

www.crayvallac.com