

CRAYVALLAC WF-1039



TECHNICAL DATA

SALES SPECIFICATION

Dropping Point
(CR 010) 110-115°C
(230-239°F)

OTHER PROPERTIES

Appearance White powder

Max particle size (CR 015) 80 µm

PRODUCT INFORMATION

CRAYVALLAC WF-1039 is a micronised PTFE modified polyethylene wax conforming to FDA 175.300. It provides the following performance based benefits:

- Excellent texturing agent
- Aids surface hardness
- Improves mar resistance
- Enhances slip

exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 4 years from production date.

PRECAUTIONS FOR USE

Please refer to the corresponding Safety Data Sheet.

RECOMMENDED AMOUNTS

Generally 0.5-3.0% based on total formulation.

INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

CRAYVALLAC WF-1039 has been especially designed to give textured finishes to polyester and hybrid powder coating systems. This texturing agent is easily incorporated using conventional pre-mixing techniques prior to extrusion.

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WF-1039** be tested thoroughly to ensure suitability for their intended end use.

PRECAUTIONS FOR STORAGE

CRAYVALLAC WF-1039 should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema
420 rue D'Estienne d'Orves
92705 Colombes Cedex - France
www.arkema.com

www.crayvallac.com