

# CRAYVALLAC WF-9710



---

## TECHNICAL DATA

### SALES SPECIFICATION

Dropping Point  
(CR 010) 110 – 115°C  
(230-239°F)

### OTHER PROPERTIES

Appearance White powder

Particle Size (CR 015)  
DV. 5 3.5-7.5 µm

---

## PRODUCT INFORMATION

**CRAYVALLAC WF-9710** is a micronised PTFE modified polyethylene wax conforming to FDA 175.300. It provides the following performance based benefits:

- Excellent slip and scuff
- High heat resistance
- Suitable for heat seal applications
- Improves anti-blocking
- Improves mar, scratch and abrasion resistance

**CRAYVALLAC WF-9710** provides the formulator with the means of controlling the frictional characteristics of a coating as well as enhancing its surface protection properties.

**CRAYVALLAC WF-9710** is suitable for use in a wide range of coating applications, and in some cases it offers the formulator additional performance benefits:

- Printing inks: enhanced heat resistance
- Powder coatings: degassing
- Metal decorating
- Coil coatings
- General industrial coatings

## RECOMMENDED AMOUNTS

Generally 0.5-3.0% based on total formulation

## INCORPORATION METHODS AND PROCESSING INSTRUCTIONS

**CRAYVALLAC WF-9710** is readily dispersed into coating formulations using a variety of techniques e.g. high-speed dispersers, bead mills and triple roll mills.

In general, micronised waxes are best incorporated into coating systems by pre-mixing with the binder. Alternatively, waxes may be added to the formulation immediately following the dispersion stage but prior to the final letdown.

Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing **CRAYVALLAC WF-9710** be tested thoroughly to ensure suitability for their intended end use.

## PRECAUTION FOR STORAGE

**CRAYVALLAC WF-9710** should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. Under these conditions the product may be stored for up to 4 years from production date.

## PRECAUTIONS FOR USE

Please refer to the corresponding Safety Data Sheet.

The information contained in this document is based on trials carried out by our technical centres and data selected from literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Arkema  
420 rue D'Estienne d'Orves  
92705 Colombes Cedex - France  
[www.arkema.com](http://www.arkema.com)

[www.crayvallac.com](http://www.crayvallac.com)